

Colorfast

integral powder colors for concrete toppings

düraamen
engineered to perform

DESCRIPTION

Colorfast is a ready-to-use, finely ground blend of synthetic iron oxide pigments and proprietary admixtures designed for coloring cementitious materials and toppings. It is used as an integral color for Pentimento, Skraffino and Pasto. It can be also used as integral color for concrete counter tops.

ADVANTAGES

- Superior we-ability, alkali resistant, curing stability and color fastness
- Unlimited variations of color through pigment blending
- Flexibility in depth and tone of the color
- UV resistant
- ASTM C 979 82 acceptable synthetic iron oxide pigments

APPLICATION

INTEGRAL COLOR

When using Colorfast always disperse pigments in the activator (Cp1000) prior to adding the cementitious powder. This process will allow for greater color consistency.

SHAKE-ON COLORING

Once perfected by the installer the shake-on coloring process allows for a more dramatic variegation in color shading. This is achieved simply by shaking on and trowelling small amounts of dry pigment into the wet mix. It is always advisable to include large mock-ups for this coloring technique prior to proceeding with the project.

COVERAGE

Colorfast is available in 10lb pails. Coverage is based upon the desired color intensity and can vary considerably. Standard dosage is from ¼ to 2 cups per pail of Pentimento, Skraffino or Pasto. One 10lb pail of Colorfast has 13 cups of colorant.

AVAILABILITY


Colorfast is available throughout the United States and Canada. Contact Düraamen representative in your area for details.

TECHNICAL SERVICE

Düraamen Engineered Products, Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.

WARRANTY

Information regarding Düraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Düraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Düraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Düraamen Engineered Products (Düraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Düraamen. If any product fails to meet this warranty, the liability of Düraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Düraamen within 1 (one) year of delivery of materials. Düraamen may in its discretion refund the price received by Düraamen in lieu of replacing the material. No customer, distributor, or representative of Düraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Düraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DÜRAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DÜRAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



düraamen engineered products, inc.

20 Haypress Road, Suite 323 Cranbury, NJ 08512 | duraamen.com | info@duraamen.com | 1.866.835.6595