

# Dekguard

## siloxane modified MMA sealer

### DESCRIPTION

Dekguard is a non-yellowing, low gloss, siloxane modified methyl methacrylate sealer for concrete surfaces. Its low viscosity allows better penetration over concrete for excellent protection. The unique formulation of Dekguard provides superior resistance to de-icing salts, salt water pool systems, rain, sleet and snow as compared to other acrylic sealers.

### ADVANTAGES

- Excellent resistant to salt water from de-icing salts and salt water pool systems
- Superior penetration and adhesion to clean, unsealed concrete surfaces
- VOC complaint for most areas in the USA and Canada
- Non-yellowing siloxane methyl methacrylate formulation

### SUBSTRATE & AMBIENT CONDITIONS

- Concrete surface must be clean and free of all contaminants and water. DO NOT apply if rain is anticipated with 24 hours of application.
- If moisture is present or if the surface is not clean and free of all contaminants, Dekguard may have white or cloudy spots and delaminate within short period of application.
- Substrate and air temperature must be no less than 40°F and not exceed 80°F. If applied outside these limits Dekguard may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, the substrate temperature can exceed 150°F which can cause extreme bubbling issues.
- Apply on cool, overcast days to avoid film formation issues. Do not apply if the temperature is expected to achieve 85°F or higher.

### APPLICATION

- Apply using a 3/8" nap roller cover using a long even uniform strokes at approximately 250-350 square feet per gallon depending on the concrete substrate. An airless sprayer containing 519 tip size may be used as well.
- Do not apply too thick or puddle. The sealer may turn cloudy or white and may never form a film. Do not apply too thin as the film may flake off or delaminate.
- Allow Dekguard to cure for 24 hours before allowing foot traffic and at least 48 hours for heavy traffic.

- Allow 4 to 6 hours between coats, if more than one coat is applied. For uniform coverage and application, two coats are recommended.
- For personal protection use gloves, respirators and protective clothing.
- It is not recommended to thin the product with any solvent.
- Please be aware that this product may be slippery when wet. We recommend addition of non-skid additives to achieve desired coefficient of friction.
- DO NOT apply near active pilot lights, sparks, heaters, smoking, electric motors or any other active source of fire.

### CLEAN UP

Use Xylene to clean the containers and tools. Dispose the consumables in accordance with local, state and federal regulations.

### COVERAGE

The first coat of Dekguard is applied 200 to 300 square feet per gallon. The second coat is applied at 300 to 400 square feet per gallon.

### MAINTENANCE

After completing the application of Dekguard, the installer should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly.


Dekguard is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Waxing is optional. Long periods of heavy traffic may cause wear patterns necessitating application of a finish coat.

### AVAILABILITY

Dekguard is available throughout the United States and Canada. Contact Düraamen representative in your area for details.

### TECHNICAL SERVICE

Düraamen Engineered Products, Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.




## TECHNICAL DATA

Percentage of active solids	15% +/- 1%
Dry Time Tack free	30 to 60 minutes @ 70°F
Dry Time Foot Traffic	4 to 6 hours @ 70°F
Dry time Heavy traffic	24 to 48 hours
Re-coat Window	4 to 24 hours
VOC	<350grams/liter
Appearance Wet	Clear
Appearance Dry	Clear low gloss
Shelf Life	1 year (unopened containers)

## WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



duraamen engineered products, inc.  
20 Haypress Road, Suite 323 Cranbury, NJ 08512 | [duraamen.com](http://duraamen.com) | [info@duraamen.com](mailto:info@duraamen.com) | 1.866.835.6595