

Perdure E32

water based epoxy emulsion primer/sealer

DESCRIPTION

Perdure E32 is a water based epoxy primer/sealer formulated to have a maximum penetration into concrete surfaces to provide high bond strength and adhesion. It is specially formulated to reduce concrete outgassing. Perdure E32 has very low odor and can be used in occupied areas. Ideal for both new and old concrete surfaces, Perdure E32 is used as a primer for Perdure high build and thin film coatings systems.

ADVANTAGES

- Low odor during application and cure
- Fast dry and re-coat time
- Easy clean-up
- Can be used on damp/green concrete
- Greatly reduces the probability of concrete outgassing

SUBSTRATE REQUIREMENTS

- Substrate temperature must be a minimum of 50°F and relative humidity below 85% for proper curing.
- Substrate must be free of dirt, waxes, curing agents and other foreign materials

COMPOSITION

Water-borne epoxy emulsion.

COLOR SELECTION

Perdure E32 is available in CLEAR formulations only.

APPLICATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in Düraamen's technical Bulletin #1. Work must be performed by trained or experienced contractors or maintenance personnel.

INSTALLATION

Mix each component of Perdure E32 prior to combining together. Mix 2 Parts A to 1 Part B for 3 minutes and allow 30 minutes of induction time.

- After the induction period, apply Perdure E32 within 45 to 60 minutes.
- DO NOT use mixed material older than its pot life.
- Mix in small quantities (1.5 gallons at a time).

Apply Perdure E32 with a short nap roller (1/4" nap) at the rate of 300ft²/gal. Care should be taken to avoid any puddles. Two coats of primer may be necessary to ensure uniform wetting and coverage. The second coat may be applied after it turns clear. Follow the recoat windows specified below:

Water based topcoat	4-24 hours
100% solids epoxy topcoat	6-24 hours
Solvent based topcoat	24 – 36 hours

CLEAN UP


Clean skin with soap and water. Tools and equipment should be cleaned with Xylene or Lacquer thinner. Consult MSDS for safety and health precautions.

COVERAGE

Perdure E32 yields 350-400ft² per gallon at 2–3 mils dry film thickness.

MAINTENANCE

After completing the installation, the applicator should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly. Perdure E32 is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Treating the surface with a floor finish (Smärtgard) is optional. Long periods of heavy traffic may cause wear patterns necessitating application of a finish coat. DO NOT leave any type of tape on the sealer for more than 5 to 10 minutes. Test first in an inconspicuous area for compatibility between the tape and the sealer.



TECHNICAL SERVICE


Dūraamen Engineered Products Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.

TECHNICAL DATA

Viscosity @ 75°F	300-400cps
Mixing Ratio	2 parts A to 1 parts B by volume
Solids Content	38-40% by volume
Bond Strength to Concrete	400-500psi (100% concrete failure)
Weight per gallon	8.75lb/gallon, mixed
Pot life	45 to 60 minutes at 70°F when mixed volume is less than 1.50 gallon
Dry to Touch	4-6 hours @ 70°F
Re-coat	6-24 hours @ 70°F
Light Traffic	24 hours @ 70°F
'H' hardness	2 days
'5-H' Hardness	30 days

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



dūraamen engineered products, inc.

20 Haypress Road, Suite 323 Cranbury, NJ 08512 | duraamen.com | info@duraamen.com | 1.866.835.6595