

Perdure U50

Solvent based Polyurethane topcoat

DESCRIPTION

Perdure U50 is a two component, chemical resistant, polyurethane topcoat/sealer. It is available in gloss and satin finishes. It offers excellent abrasion, chemical and stain resistance, and superior color retention. It is ideal for concrete substrates in garages, restaurants, warehouses, storage facilities, aircraft hangars, animal housing and vehicle maintenance facilities.

ADVANTAGES

- Excellent abrasion, chemical and stain resistance
- Superior hot-tyre pick-up resistance
- Suitable for both exterior and interior applications
- May be used for both horizontal and vertical applications

SUBSTRATE REQUIREMENTS

- Substrate temperature must be a minimum of 50°F and relative humidity below 85% for proper curing.
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Cure times will be extended in conditions of high humidity and poor ventilation

COMPOSITION

Perdure U46 is formulated based on aliphatic polyisocyanate.

COLOR SELECTION

Perdure U50 is available in CLEAR and limited pigmented formulations. Custom colors are available subject to laboratory approval, minimum quantity, lead time for production and increased cost.

APPLICATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in Düraamen's technical Bulletin #1. Work must be performed by trained or experienced contractors or maintenance personnel

INSTALLATION STEPS

Mix each component of Perdure U50 prior to combining them together. Mix 2 parts of Part A and 1 Part B. Perdure U50 is usually applied with a brush, short nap roller, or squeegee and back-rolled with a short nap roller. Care should be taken to minimize the entrapment of air caused by over-rolling. Perdure U50 can also be applied by airless or conventional spray.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with Xylene or Lacquer thinner. Consult MSDS for safety and health precautions.

COVERAGE


Perdure U50 yields 350-400ft² per gallon at 2-3 mils dry film thickness. Applying thicker than 3 mil in one pass may result in bubbles or pin holes. Recoat time is approximately 14-16 hours at 75°F.

AVAILABILITY

Perdure U50 is available throughout the United States and Canada.

MAINTENANCE

After completing the installation, the applicator should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly. Perdure U50 is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Treating the surface with a floor finish (Smärtgard) is optional. Long periods of heavy traffic may cause wear patterns necessitating application of a finish coat.



TECHNICAL SERVICE

Düraamen Engineered Products Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.

TECHNICAL DATA

Viscosity @ 75°F	700-900cps
Mixing Ratio	2 parts A to 1 parts B by volume
Solids Content	56% clear and 65% pigmented
VOC	405gm/lt
Weight per gallon	10.5lb/gallon, mixed
Pot life	2 hours @ 75°F
Dry to Touch	10-14 hours @ 75°F
Re-coat	12-16 hours @ 75°F
Light Traffic	24 hours @ 75°F
Full Cure	7-10 days

CHEMICAL RESISTANCE CHART

REAGENT	RATING
Acetic Acid – 5%	L
Acetone	L
Betadine	R
Beer	R
Brake Fluid	R
Bleach	L
Citric Acid – 30%	R
Citric Acid – 40%	L
Crude Oil	R
Diesel Fuel	R
Ethylene Glycol	R
Fatty Acids	L
Gasoline	R
Hydrochloric Acid – 15%	R
Lactic Acid – 15%	R
Lactic Acid – 50%	L
Methyl Ethyl Ketone	L
Nitric Acid – 10%	R
Orange Juice	R
Peroxide – 35%	R
Phosphoric Acid – 85%	L
Skydrol	R
Sodium Hydroxide – 50%	R
Sulfuric Acid – 20%	R
Toluene	R
Urea	R
Vinegar	L
Xylene	L
Iodine	


R – Recommended for continuous service

L – Limited recommendation, occasional spills

* - May cause slight stain or discoloration

WARRANTY

Information regarding Düraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Düraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Düraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Düraamen Engineered Products (Düraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Düraamen. If any product fails to meet this warranty, the liability of Düraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Düraamen within 1 (one) year of delivery of materials. Düraamen may in its discretion refund the price received by Düraamen in lieu of replacing the material. No customer, distributor, or representative of Düraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Düraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



düraamen engineered products, inc.

20 Haypress Road, Suite 323 Cranbury, NJ 08512 | duraamen.com | info@duraamen.com | 1.866.835.6595