

Perdure PU85

polyurea-polyurethane coating

DESCRIPTION

Perdure PU85 is a two-component high-solids polyurea polyurethane coating formulated to be used in high-traffic areas. It is a very low VOC, no odor, flexible and impact resistant, and UV stable coating. It cures rapidly, allowing for a quick return to service. Its enhanced cross-linking properties create excellent adhesion to the concrete substrates.

ADVANTAGES

- Self-Priming
- Rapid cure, Quick return to service
- High impact resistance
- Excellent bond with substrates
- Simple Mix ratio (1:1)
- Resistant to fading (UV stable)

IMPORTANT CONSIDERATIONS

- Substrate temperature must be a minimum of 50°F
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Do not apply over damp or wet substrates
- Avoid applications on surfaces with active moisture vapor transmission

COMPOSITION

Two-component Polyurea-Polyurethane

SURFACE PREPARATION

1. The substrate must be free from any dirt, grease, oil and other contaminants.
2. A CSP of 3 or 4 must be achieved before applying Perdure PU85
3. Ensure that the substrate temperature is at least 50°F
4. The substrate must be free from any moisture vapor emission
5. Address cracks in the concrete substrate before applying Perdure PU85

INSTALLATION STEPS

1. Mix Part A with Part B at 1:1 mix ratio
2. Mix only that amount that can be used within 15 minutes
3. Add the desired amount of color after mixing Part A and Part B for 30 to 45 seconds. Mix again for 1 to 2 minutes to achieve a homogenous mix.
4. Pour the mixed material onto the substrate immediately after mixing. Leaving the mixed material in the container reduces the pot life significantly. For color consistency from batch to batch, Part A can be mixed with color before mixing with Part B.
5. Pour the mixed material into 8 to 12" wide strips and spread it with a notched squeegee to achieve the desired thickness. Immediately back-roll the spread material with a 1/4" to 3/8" nap roller.
6. Precut the edges of the floor with a chip brush.
7. For decorative floors broadcast resin chips or Kwartz within 15 minutes of spreading the material
8. Allow Perdure PU85 to cure for at least 4 to 6 hours before proceeding to the next step.
9. The working time will be reduced under high temperatures and/or humid conditions

CLEAN UP

Clean skin with soap and warm water. Tools and equipment should be cleaned with Xylene or lacquer thinner. Consult SDS for safety and health precautions.

COVERAGE


One gallon of Perdure PU85 covers 150 to 160 sq.ft, at 10 mil thickness.

PACKAGING

Perdure PU85 is available in 2.0 gal and 10.0 gal Kits.

TECHNICAL SERVICE

Duraamen Engineered Products provides series and consultations, selection, specification, troubleshooting and other information on the proper repair and protection of surfaces.



TECHNICAL DATA

	Category	5°C (40°F)	20°C (70°F)	30°C (85°F)
Drying time	Set-to-touch	5 hours	1.5 hours	1 hour
	Dry-through	18 hours	6 hours	4 hours
	Pot life	30 minutes	20 minutes	10 minutes
	Over-coat (Min.)	-	8 hours	6 hours
	Over-coat (Max.)	-	24 hours	18 hours

The above drying times have been measured under laboratory conditions and may vary depending on the construction site.


Viscosity	Not Applicable	Color	Clear
Specific gravity	approx.. 1.08 (mixture)	Solid volume	approx. 85%
Mixing ratio	A / B = 1 / 1 (Volume ratio)	Shelf life	12 months indoor storage at 5~35°C (40°~95°F)

Product Properties (Physical Property Data)

Adhesion	600 (psi) (substrate ruptures)	Hardness	Shore D 60 ± 10
Tensile strength	> 2000 (psi)	Tear strength	> 50 (N/mm)
Abrasion resistance	< 150 (mg) (ASTM D4060 CS17/1000cycles/1000g)	Elongation at break	50~100%

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



duraamen engineered products, inc.

20 Haypress Road, Suite 323 Cranbury, NJ 08512 | duraamen.com | info@duraamen.com | 1.866.835.6595